



# Twin Ports Testing Inc.

1301 N. 3rd Street • Superior, WI 54880 • 715-392-7114 • Fax 715-392-7163  
218-722-1911 • 800-373-2562 • www.twinportstesting.com

## Big Heat Fuel Pellets

5601 Industrial Avenue  
Rockford, Illinois 61111

Date Received: 8/16/2008

Date Reported: 8/20/2008

Purchase Order #:

Attn: Claire Brant

Sample Log Number: 08C1957

Sample Designation: Pellets

	MOISTURE & ASH FREE	MOISTURE FREE	AS RECEIVED	UNITS	METHOD
Moisture Total			5.18	% wt.	ASTM E871
Ash		0.26	0.24	% wt.	ASTM E1102
Sulfur		0.01	0.01	% wt.	ASTM D4239
Heating Value	8118	8097	7678	Btu/lb	ASTM E711

Prepared By:

*Ken Anderson*

Date:

*8/21/08*